



1L | 1324101-001

RAVENOL AHC Active Height Control Fluid

Kategorie: Car hydraulic oil

Artikelnummer: 1324101

Oil type: Synthetic

Recommendation: Nissan KLG01-00501EU, Nissan KLG01-00502, Toyota AHC-Fluid 08886-01805, Toyota AHC-Fluid 08886-81260

Application: Passenger car

RAVENOL AHC Active Height Control Fluid is a full synthetic hydraulic fluid based on PAO (Poly-alpha-olefin) and Ester.

RAVENOL AHC Active Height Control Fluid is used as suspension fluid for active height control systems (AHC) for vehicles from Toyota and Lexus as well as for HBMC systems (Hydraulic Body Motion Control) from Nissan and Infiniti.

Application Note

RAVENOL AHC Active Height Control Fluid is used in vehicles from Toyota, Lexus, Nissan and Infiniti that are equipped with an active height control system. This system was designed not only to change the position of the suspension system, but also to give the car a special softness.

RAVENOL AHC Active Height Control Fluid is especially suitable for the active control system of vehicles from Toyota, Lexus, Nissan and Infiniti. The AHC system holds approx. 4.5 liters. The change with **RAVENOL AHC Active Height Control Fluid** should take place approx. every 90,000 km. Oil change intervals according to the manufacturer's instructions.

RAVENOL AHC Active Height Control Fluid is suitable for use in the following vehicles: Toyota Land Cruiser 100 and 200, Lexus LX470 and LX570, Nissan Patrol, Infiniti QX.

Warning:

Never use brake fluid instead of **RAVENOL AHC Active Height Control Fluid**. This leads to the erosion of polymer seals of the system.

Characteristics

- A high performance level
- A very good viscosity temperature behaviour
- A high aging resistant
- An excellent wear protection
- A solid corrosion protection
- Neutral towards sealing materials

Technical Product Data

PROPERTY	UNIT	DATA	AUDIT
Viscosity at 100 °C	mm²/s	2,85	DIN 51562-1
Viscosity at 40 °C	mm²/s	10,28	DIN 51562-1
Viscosity Index VI		132	DIN ISO 2909
Pourpoint	°Celsius	-60	DIN ISO 3016
Colour		hellrot	VISUELL
Seq. I at 24 °C		0/0	ASTM D892
Seq. II at 93,5 °C		0/0	ASTM D892
Seq. III at 24 °C after 93,5 °C		0/0	ASTM D892
tbn		2,38	DIN ISO 2909
VKA Four Ball Test (Wear)	mm	0,45	ASTM D2896
	mm²/s	10,28	DIN EN ISO 20623
	mm²/s	2,85	DIN EN ISO 20623
Copper Strip Test at 150 °C		1a	ASTM D130
Flashpoint	°Celsius	195	DIN EN ISO 2592

All indicated data are approximate values and are subject to the commercial fluctuations.

Alle angegebenen Daten sind ca. Werte und unterliegen handelsüblichen Schwankungen.

30.05.2023