

# RAVENOL Mehrzweckfett mit MoS-2

**Kategorie:** Grease

**Artikelnummer:** 1340103

**Specification:** DIN 51502: KPF2K-30, ISO 6743-9: ISO-L-XCCIB2

**Application:** Passenger car, Truck, Agricultural machinery, Industry

**RAVENOL Mehrzweckfett mit MoS2** is a lithium saponified multipurpose grease with finely divided MoS2 to increase heavy loads at very high temperatures.

**RAVENOL Mehrzweckfett mit MoS2** is formulated with a highly refined base oil mixture which contains less than 3% polycyclic aromatics.

The optimized formulation of **RAVENOL Mehrzweckfett mit MoS2** has distinctive friction-reducing properties and so-called dry running properties.



**0.1L | 1340103-100**

**0.4L | 1340103-400**

**1L | 1340103-001**

**5L | 1340103-005**

**10L | 1340103-010**

**15L | 1340103-015**

**25L | 1340103-025**

**180L | 1340103-180**

## Application Note

**RAVENOL Mehrzweckfett mit MoS2** has been designed for applications exposed to extreme pressure and shock loaded bearings with relatively slow sliding movements.

**RAVENOL Mehrzweckfett mit MoS2** is recommended for friction and roller bearings of all types during aggravated operating conditions.

**RAVENOL Mehrzweckfett mit MoS2** is also used for chassis lubricating.

## Characteristics

- Extreme shear stability
- Excellent corrosion protection
- Very good mechanical and chemical stability
- Very good aging resistant
- Good pump output also at low temperatures

## Technical Product Data

| PROPERTY                                | UNIT               | DATA                  | AUDIT        |
|-----------------------------------------|--------------------|-----------------------|--------------|
| Colour                                  |                    | schwarz-grau          | VISUELL      |
| Thickener                               |                    | Lithium-Komplexseifen | DIN 51757    |
| Additives                               |                    | Molybdändisulfid      | DIN 51757    |
| NLGI-Class                              |                    | 2                     | DIN 51818    |
| Product Classification                  |                    | KPF2K-30              | DIN 51502    |
| Working Temperature                     | °C                 | -30 / +120            | DIN 51825    |
| Short term temperature up to            | °C                 | 130                   | DIN 51757    |
| Worked Penetration at 60 Strokes        | mm/10/25°C         | 265-295               | ISO 2137     |
| Corrosion (SKF Emscor dist. Water)      | Korr. Grad         | 1                     | DIN 51802    |
| Dropping Point                          | °C                 | >180                  | DIN ISO 2176 |
| Copper Corrosion (24h/120 °C)           |                    | 1                     | DIN 51811    |
| Water Resistance (3h/90 °C)             | °C                 | 1-90                  | DIN 51807-1  |
| VKA Pressure Carrying Capacity          | N                  | 2800 - 3000           | DIN 51350-4  |
| Kinematic Viscosity (Base Oil) at 40 °C | mm <sup>2</sup> /s | 80                    | DIN 51562-1  |

All indicated data are approximate values and are subject to the commercial fluctuations.

**Alle angegebenen Daten sind ca. Werte und unterliegen handelsüblichen Schwankungen.**

31.05.2023